



Landscape Horticulture,
Sport and Recreation Materials
MACKA'S RACECOURSE SAND



Macka's Racecourse sand has been tested and passed specifications for Professional Sand Horse Tracks. Stability is the key to suitable product and the below size distribution indicates a suitable range for high wear tracks. Macka's Racecourse Sand has also been compared to three other racecourse sands currently used with excellent results.

	Spec % passing	Mackas
2.36	100	100
1.18	95 - 100	100
.600	85 – 100	100
.425	50 – 95	95
.300	30 – 70	53
.150	0 – 20	1
75micr	0 - 5	0

Particle size	Sand A % by wt.	Sand B % by wt	Sand C % by wt	Sand D % by wt	Macka's Racecourse Sand % by wt
> 2.0mm	0	0	0		0
1.0-2.0mm	0.6	0.5	0.2	1.9	0.1
0.5-1.0mm	9.2	13.2	11.8	18.0	1.3
0.25-0.5mm	69.4	66.8	67.5	62.2	85.5
0.10- 0.25mm	19.1	17.6	19.5	16.9	13.2
<0.10mm	0.9	1.9	1.0	1.0	0.1
Stability 16 drops	8.33	9.83	7.37	11.68	9.55
Reading 32 drops	5.26	6.01	4.56	8.1	6.2

NB: The information provided in this product guide should be used as a guide only. For further details or for design and application support, please contact us.

P: +61 2 4982 6227 | E: sales@mackassand.com.au | www.mackassand.com.au